

# Carbon BLACK N 330

Appearance: Black power or granular

## Specification:

Iodine Absorption Number (g/Kg) : 77-88

Absorption Value of DBP ( $10^{-5} \text{M}^3/\text{Kg}$ ) : 97-107

Absorption Value of compressing sample DPB ( $10^{-6} \text{M}^3/\text{Kg}$ ) : 83-93

Adsorptive Specific Surface Area of CATB ( $10^3 \text{M}^2/\text{Kg}$ ) : 77-87

Adsorptive Specific Surface Area of Nitrogen ( $10^3 \text{M}^2/\text{Kg}$ ) : 78-88

Tinting Strength : 98-108%

Heating Loss: 2.5% max

Ash : 0.5% max

Tensile Strength:  $\geq 0.5$  MPa min

300% Extending stress:  $-1.0 \pm 1.0$  MPa

Packing: 25kg/bag, 16MT/ 20'FCL