

Quality characteristics of goods:

PROPERTIES	ASTM test method	Limits	Actual
Iodine absorption number, g/kg	D 1510	82+/-5	83,6
Oil absorption number, cm ³ /100g	D 2414	102+/-5	101,3
CTAB surface area, m ² /g	D 3765	82+/-5	80,5
Sieve residue 45 µm (No.325), %,max	D 1514	0.1	0,00
Sieve residue 500 µm (No.35) %, max	D 1514	0.001	0.0000
Heating loss, %, max	D 1509	1.0	0,15
Ash content, %, max	D 1506	0.75	0,24
Pour density, kg/m ³	D 1513	380+/-25	397
Fines content, %, max	D 1508	7.0	3,2
Tint strenght	D 3265	104+/-5	104,0
Manufacturing date			8/22/2008

NET WEIGHT: 26000.00 KG
 GROSS WEIGHT: 26208.00 KG
 NO OF PACKAGES: 1040 BAGS